

Water Adsorption on Actinide Oxide Surfaces

Bengt Tegner
School of Chemistry
The University of Manchester

DISTINCTIVE 2nd Annual Meeting
19th April 2016
Bristol



Outline

- Motivation
- Computational Method
- Results and Discussion
- Conclusions and Future Work
- Acknowledgements

Motivation

- The UK's stock of civil plutonium is stored as PuO_2 powder in multi layer steel cans in Sellafield.
- Under certain circumstances, gas generation may occur within the cans, with consequent pressurisation.

*“worker performing general housekeeping and relocating storage cans in the interim storage vault noticed a plutonium bearing storage can was **bulging on both ends**”*

Lawrence Livermore National Laboratory 1994



- Several proposed routes to gas production, including:
 - (i) steam produced by H_2O desorption from hygroscopic PuO_2 due to self-heating
 - (ii) radiolysis of adsorbed water
 - (iii) generation of H_2 by reaction of PuO_2 with H_2O , producing a “postulated” PuO_{2+x} phase


All involve $\text{PuO}_2/\text{H}_2\text{O}$ interactions and are complex, inter-connected and poorly understood

⇒ Model the interaction of water on PuO_2 surfaces at the atomic level

- method development
- initial results


Computational Method

- Density Functional Theory
- VASP 5.4.1
- PAW-pseudopotentials
- Plane wave basis set
- k-point sampling of 1st BZ
- Spin-polarised
- $\text{DFT}+U = \text{PBE}+U$




Computational Method

- Surfaces are modelled using a repeating slab of 24 AnO_2 units with 18 Å of vacuum between each slab.
- Water is adsorbed on both sides of the slab to ensure the system has no net dipole moment.




Results: Water on UO_2 / CeO_2 (111)




Molecular

25% coverage = $\frac{1}{4}$ ML




Dissociative

Results: Water on UO_2 / CeO_2 (111)




Molecular

50% coverage = $\frac{1}{2}$ ML




Dissociative

Results: Water on UO_2 / CeO_2 (111)




Molecular

75% coverage = $\frac{3}{4}$ ML




Dissociative

Results: Water on UO_2 / CeO_2 (111)



Molecular

100% coverage = 1 ML



Dissociative

Results: Water on UO₂ (111)

Coverage	UO ₂ (111) @ 0.25 ML	UO ₂ (111) @ 0.50 ML	UO ₂ (111) @ 0.75 ML	UO ₂ (111) @ 1.00 ML
H ₂ O / nm ²	1.95	3.89	5.84	7.78
mg / m ²	0.058	0.12	0.17	0.23

Results: Water on UO_2 (111)

System	U_{eff} (eV)	0.25 ML	0.5 ML	0.75 ML	1.0 ML
$\text{UO}_2 + \text{H}_2\text{O}$	4.0	-0.53	-0.53	-0.53	-0.49
$\text{UO}_2 + \text{OH} + \text{H}$	4.0	-0.50	-0.41	-0.29	-0.15
$\text{UO}_2 + \text{H}_2\text{O}$ [1]	4.0	-0.61	N/A	N/A	-0.60
$\text{UO}_2 + \text{OH} + \text{H}$ [1]	4.0	-0.68	N/A	N/A	-0.32

[1] T. Bo, J. Lan, Y. Zhao, Y. Zhang, C. He, Z. Chai and W. Shi, *J. Nucl. Mat.* **454** (2014) 446-454

Results: Water on UO_2 / CeO_2 (111)

System	U_{eff} (eV)	0.25 ML	0.5 ML	0.75 ML	1.0 ML
$\text{UO}_2 + \text{H}_2\text{O}$	4.0	-0.53	-0.53	-0.53	-0.49
$\text{UO}_2 + \text{OH} + \text{H}$	4.0	-0.50	-0.41	-0.29	-0.15
$\text{CeO}_2 + \text{H}_2\text{O}$ [2]	5.0	-0.56	-0.60	N/A	-0.57
$\text{CeO}_2 + \text{OH} + \text{H}$ [2]	5.0	-0.59	N/A	N/A	-0.15



[2] M. Molinari, S. C. Parker, D. C. Sayle, and M. S. Islam,
The Journal of Physical Chemistry C **2012** 116 (12), 7073-7082

Results: Water on UO_2 / CeO_2 (111)

Distance (Å)	UO_2	CeO_2 [2]
$\text{H}_\text{W} - \text{O}_{1\text{S}}$	1.96 – 2.28	1.99 – 2.13
$\text{U}_{1\text{S}} / \text{Ce}_{1\text{S}} - \text{O}_\text{W}$	2.62 – 2.69	2.62
$\text{U}_{1\text{S}} / \text{Ce}_{1\text{S}} - \text{O}_\text{W}\text{H}_\text{W}$	2.18 – 2.26	2.22
$\text{U}_{1\text{S}} / \text{Ce}_{1\text{S}} - \text{O}_{1\text{S}}\text{H}_\text{W}$	2.33 – 2.44	2.41
$\text{O}_{1\text{S}}\text{H}_\text{W} - \text{O}_\text{W}\text{H}_\text{W}$	1.61 – 2.39	1.65



[2] M. Molinari, S. C. Parker, D. C. Sayle, and M. S. Islam,
The Journal of Physical Chemistry C **2012** 116 (12), 7073-7082

Results: Water on UO_2 / CeO_2 (110)





Molecular
25% Coverage = $\frac{1}{4}$ ML

Results: Water on UO_2 / CeO_2 (110)




Molecular
50% Coverage = $\frac{1}{2}$ ML

Results: Water on UO_2 / CeO_2 (110)




Molecular
100% Coverage = 1 ML


Results: Water on UO_2 / CeO_2 (110)




Dissociative
25% Coverage = $\frac{1}{4}$ ML




Results: Water on UO_2 / CeO_2 (110)




Dissociative
50% Coverage = $\frac{1}{2}$ ML



Results: Water on UO_2 / CeO_2 (110)



Dissociative
100% Coverage = 1 ML



Results: Water on UO₂ (110)

Coverage	UO ₂ (110) @ 0.25 ML	UO ₂ (110) @ 0.50 ML	UO ₂ (110) @ 1.00 ML
H ₂ O / nm ²	1.17	2.35	4.70
mg / m ²	0.035	0.070	0.14

Results: Water on UO_2 / CeO_2 (110)

System	U_{eff} (eV)	0.25 ML	0.5 ML	1.0 ML
$\text{UO}_2 + \text{H}_2\text{O}$	4.0	-0.93	-0.74	-0.65
$\text{UO}_2 + \text{OH} + \text{H}$	4.0	-1.39	-1.05	-1.00
$\text{CeO}_2 + \text{H}_2\text{O}$ [2]	5.0	-0.85	-0.76	N/A
$\text{CeO}_2 + \text{OH} + \text{H}$ [2]	5.0	-1.12	-1.00	-0.21

[2] M. Molinari, S. C. Parker, D. C. Sayle, and M. S. Islam,
The Journal of Physical Chemistry C **2012** 116 (12), 7073-7082

Results: Water on UO_2 / CeO_2 (110)

Distance (Å)	UO_2	CeO_2 [2]
$\text{H}_\text{W} - \text{O}_{1\text{S}}$	2.19 – 2.26	2.07
$\text{U}_{1\text{S}} / \text{Ce}_{1\text{S}} - \text{O}_\text{W}$	2.73 – 2.79	2.67
$\text{U}_{1\text{S}} / \text{Ce}_{1\text{S}} - \text{O}_\text{W}\text{H}_\text{W}$	2.17	2.14
$\text{U}_{1\text{S}} / \text{Ce}_{1\text{S}} - \text{O}_{1\text{S}}\text{H}_\text{W}$	2.59	2.48 – 2.58
$\text{O}_{1\text{S}}\text{H}_\text{W} - \text{O}_\text{W}\text{H}_\text{W}$	2.36	1.92

[2] M. Molinari, S. C. Parker, D. C. Sayle, and M. S. Islam,
The Journal of Physical Chemistry C **2012** 116 (12), 7073-7082

Conclusions and Future Work

- Studying the actinide oxides using DFT remains a challenge.
- Careful use of the DFT+ U method allows calculation of structural and electronic properties.
- First results on the $\text{UO}_2(111)$ and (110) surfaces suggest molecular adsorption on the (111) surface and dissociative adsorption on the (110) surface.
- Future work will focus on adsorption energies on the (100) uranium dioxide surface, followed by reduced surfaces.

Acknowledgements

Nik Kaltsoyannis, University of Manchester

Andy Kerridge, Lancaster University

Jeff Hobbs, Sellafield Ltd

Helen Steele, Sellafield Ltd

Howard Sims, National Nuclear Laboratory

Results: Dry UO₂ Surfaces

Surface Energy	UO ₂ (111)	UO ₂ (110)	UO ₂ (100)
meV / Å ²	40.76	65.69	82.79
J / m ²	0.65	1.05	1.33
J / m ² [3]	0.78	1.05	1.47

[3] Zs. Rák, R.C. Ewing, and U. Becker, *Surface Science*, **608**, (2013), 180-187